

# **LAMINATED ELECTRONIC COMPONENT AND MANUFACTURING METHOD THEREFOR**


**Patent number:** JP2003017356  
**Publication date:** 2003-01-17  
**Inventor:** IWAIDA TOMOHIRO  
**Applicant:** KYOCERA CORP  
**Classification:**  
 - International: **B32B7/02; H01G4/12; H01G4/30; B32B7/02; H01G4/12; H01G4/30; (IPC1-7): H01G4/12; B32B7/02; H01G4/30**  
 - european:  
**Application number:** JP20010197119 20010628  
**Priority number(s):** JP20010197119 20010628

Report a data error here

## **Abstract of JP2003017356**

**PROBLEM TO BE SOLVED:** To provide a laminated electronic component where a step due to the thickness of an inner electrode layer can be eliminated and the occurrence of a crack and delamination can be suppressed even if a dielectric ceramic layer is thinned and the number of laminations is increased, and to provide the manufacturing method.

**SOLUTION:** The inner electrode layer 9 and an inner electrode layer extending part 11 form the same plane which does not substantially have a step. The dielectric ceramic layer 7b of a non-capacity part 3 is constituted of a ceramic having sintering property higher than the dielectric ceramic layer 7a of a capacity part 1.



Data supplied from the esp@cenet database - Worldwide

